THE EXPRESSIVE POWER OF WOOD



Collection 2024

 \geq

200X1200MM


Experience the calmness and elegance of nature from the comfort of your own home. Discover the strength, textures, and tones that wood has to offer. The collection of 200x1200mm tiles is everything different you were looking for.



HAZY

SERIES












SOLUTION TO ALL YOUR DESIGN NEEDS

Geo Gres offers a complete solution for porcelain floors and walls that consist of excellent technical performance and unique aesthetic appeal.

The variety and complete range of Geo Gres porcelain meets your needs of contemporary planning for indoor and outdoor design solution.





OUR COLLECTION. YOUR CREATION.

HAZY



OAK PINE SANDLE SILVER TEAK WALNUT

AMBER






HAZY AMBER



Size 200x1200mm 20x120cm

18 Random











HAZY OAK



Size 200x1200mm 20x120cm

18 Random









HAZY PINE



Size 200x1200mm 20x120cm

18 Random







HAZY SANDLE

HAZY SANDLE

Size 200x1200mm 20x120cm

18 Random









HAZY SILVER



Size 200x1200mm 20x120cm

18 Random











Size 200x1200mm 20x120cm

18 Random







HAZY WALLNUT




Size 200x1200mm 20x120cm

18 Random





LAYING SOLUTIONS




The material should be carefully checked before fixing, especially tonality, caliber and choice. Claims cannot be accepted once the material is installed. The company declines all responsibility for laying without joints; minimum joint laying has a gap of 2 mm.

PORCELAIN STONEWARE - STANDARD EN 14411 (ISO 13006) ANNEX G GROUP BIA, E 0.5%

TECHNICAL SPECIFICATIONS			STANDARDS	VALUES REQUIRED	OUR Values
				RECTIFIED	MATT
DIMENSIONS		Length and width	- ISO 10545-2	<u>+</u> 0,3%, max 1 mm	In According
		Thickness		<u>+</u> 5%, max 0,5 mm	In According
		Wedging		<u>+</u> 0,3%, max 1,5 mm	In According
		Straightness of the edges		<u>+</u> 0,3%, max 0,8 mm	In According
		Flatness		<u>+</u> 0,4%, max 1,8 mm	In According
STRUCTURE	• 	Water absorption – average value %	ISO 10545-3	<u>≤</u> 0,5%	In According
		Breaking strength	- ISO 10545-4	S <u>≥</u> 1300 N	S <u>≥</u> 2000 N
		Modulus of rupter		R≥ 35 N/mm²	In According
		Resistance to surface abrasion	ISO 10545-7	According to classification indicater by manufacture	PEI IV
THERMAL SHOCK		Coefficient of thermal linear expansion	ISO 10545-8	9 x 10 ⁻⁶ max	In According
		Thermal shock resistance	ISO 10545-9	Resistant	Resistant
		Resistance to frost	ISO 10545-12	Resistant	Resistant
SAFETY		Dynamic friction coefficient	DIN 51130	According to the space or the working area	R9
CHEMICAL RESISTANCE	•	Resistance to high concentrations of acids and alkalis	ISO 10545-13	Class GHC Min.	Class GHA
		Resistance to low concentrations of acids and alkalis		Class GLC Min.	Class GLA
		Stain resistance	ISO 10545-14	Min. class 3	5




INSTALLATION ADVICE



The longest side should be staggered no more than 300mm when laid in running bond.






The V-Shade classification indicates the level of shading of the product, ranked from V0 to V4.

PACKAGING









Delta Tiles Ltd.

8 A National Highway Opp. 132 kva Sub- Station, At lalpar, Morbi - 363642, Gujarat, INDIA.

Export Enquiry : +91 98256 04212 | export@geogres.in Domestic Enquiry: +91 97277 04212 | info@geogres.in

www.geogres.in

